



Technical Specification Sheet

MALMO

WWW.JMTLEATHER.COM.CN

WWW.JMTLEATHER.COM

MALMO:



Smooth pure aniline leather vacuum dried to give a full hand feel. The sheen and depth produced during processing is continuously enhanced through use. Suitable for domestic and light wear contract market. Substance 0.9/1.0mm. Average size about 60 sqft. Made on South German bull hides.

100% Made in Italy

COLOUR SELECTION:



SAVANNE
3000

PORCELAIN
9265

SAND
2815

SAHARA
3811

CAMEL
2476

NOUGAT
2496

COGNAC
2488



BRONZE
2202

TEAK
2057

ESPRESSO
2040

PEAT
3301

BLACK
0500

MARBLE
1414

TAUPE
1011



LIGHT-OLIVE
3007

REED
3455

FANGO
7032

MINT
7070

CHERRY
4458

LAVENDER
6060

INDIGOBUE
5470



INDIUM

EISLCE

FLINT

TERRA

HONIGHONEY

DARK
CHOCOLATE

HOUNDER
ELDERBERRY

1050

1081

1115

2109

3131

3363

4275



PATINA

TIEFESMEER
DEEPWATER

GREENSTONE

BAMBAUS
BAMBOO

KARDAMOM

5241

5415

7246

7547

8520

For Leather swatch, please contact JMT sales team.

GENERAL DETAILS

Category	Aniline
Application	Furniture
Raw Material	South Germany Bulls
Country of Production	Italy
Average Hide Size sq ²	About 60
Average Thickness mm	0.9-1.0
Colour Checking	D65 Daylight
Appearance	Conform to the master

CHARACTERISTIC	TEST METHOD	M.U.	PERFORMANCE
Thickness	ISO2589	mm	0.9-1.0
Dry Rub Fastness	EN ISO 11640	Grey scale	Dry 50 cycles >3
Wet Rub Fastness	EN ISO 11640	Grey scale	Wet 20 cycles >3
Perspiration Rub Fastness	EN ISO 11641	Grey scale	Perspiration 20 cycles > 3
Finishing Adhesion	ISO 1164	N/10mm	>2
Flexing Endurance	EN ISO 5402	Visual	Dry 20,000 cycles (no cracks)
Colour Fastness to Light	EN ISO 105-B02	Blue Scale	>3
Tear Strength – Single edge	EN ISO 3377-2	N	>20
Tensile Strength	EN ISO 3376	N/mm ²	>10
Colour Fastness to Water Spotting	EN ISO 15700	Grey Scale	>3
pH and ΔpH	EN ISO 4045	Min 3,2 - ΔpH≤0.7 if pH<4	Pass
Burning Behaviour to cigarette and match flame	BS 5852:1979-BS EN 1021-1/ EN 1021-2		Pass
Chemical Characteristic	Article processed in conformity with Reach regulation		

LEATHER FEATURES AND CARE:

Characteristics not presented in this document are not applicable or not defined by producer. Additional requirements must be specified by the Customer before making the purchase order. Results of tested characteristics are an average of results found on standard productions. Eco and Environmental safety conformity to CE 1907/2006 REACH is assured until shipment. In case of further chemical treatments, it is the customer's responsibility to verify the chemical compatibility and that the chemicals used, do not impact on the conformity of the leather. JMT Leather will not respond legally in case of missed indications checking. Hides must be worked maintaining an internal humidity of the hide of 10-12% and using a process temperature not higher than 60°C/140°F to avoid any change of the hides mechanical properties and aspect. Do not put over weights on hides during stock, same goes for finished furniture. Stock hides and finished furniture in dry ambient with temperature 15/40°C - 59/104°F. Avoid using any solvent or lotion because they could weaken finishing adhesion. Heat guns shrink wrapping and any other source of heat must be avoided. Avoid using any wrapping/packing material that may react with the leather or finished furniture. Natural growth features, colour and structure differences (uneven appearance) are indications of genuineness (visible/clearly visible). Natural defects such as scars, growth marks and insect bites are normal hide characteristics and are not part of the leather production process. The initial leather smell is typical of the material. Colour and structure differences compared with the sample furniture and leather specimens are possible. To maintain the initial characteristics of goods produced with our articles, it is recommended to follow these instructions: keep them in dry ambient at room temperature. Keep leather away from sunlight and from any sources of heat to avoid colour change and darkening.

Use only recommended leather cleaner and protector products. Totally avoid multi-purpose cleaning products. Before using cleaning product, try it on a hidden surface. Clean stains as fast as possible; beverage stains could be removed dabbing with blotting paper without rubbing, then pass gently a white wet cloth on the stain, from external to internal side. After drying, polish it with a soft dry cloth. For domestic furniture, fully

clean and re-protect your leather furniture at least every six months. For contract furniture, we recommend a regular cleaning and maintenance program as often as necessary.

We recommend leather maintenance products by LCK International in Germany.

PRODUCT APPLICATION:





CONTACT US:

Tianjin Main Office

E19 Universal Enterprise Park, No. 1 Si Zhi Road,
Universities Industrial Zone, Jingwu Town, Xiqing District,
Tianjin, 300382. (JMT China Center)
Tel: +86 (022) 2825 3667 Fax: +86 (022) 2822 9114
Email: salescn@jmtleather.com.cn

Shanghai Office

Room 1207 ,Zhonghuamen Building , No.520 Yishan Road,
Xuhui District,Shanghai,China 200030
Tel : (+86) 021 60831155-132, 18516022339
Email: salescn@jmtleather.com.cn

Singapore Office

74A Meyer Road
Singapore 437900
Tel: +65 8403 8168
Email: sales@jmtleather.com

Melbourne Office

Tel: +61(0)433 033 890
Email: sales@jmtleather.com
Email: lisa@jmtleather.com.au

