



WWW.JMTLEATHER.COM.CN

WWW.JMTLEATHER.COM

MILANO II COLLECTION:



Bold and contemporary range of leathers has been developed in conjunction with leading design experts for all contract applications. Made on better quality corrected grain hides and finished with a pigmented topcoat, which is lightly embossed with an artificial grain pattern. We have added a further 57 colours to our Milano collection, suitable for all domestic and contract applications. Substance 0.9/1.0 mm. Average size about 55 sqft. Made on European Ox hides.

100% MADE IN ITALY.

COLOUR SELECTION:



Cotton 9976

White9998

Vanilla2100

Butter2999

Buttercream 2979

Blue grey 1020

Jadegrey 1991



Jadegreen 5191

Jadeblue 5670

Lagoon 7835

Pine 7005

Kale 5225

Seagras 7540

Amazonas 7810



Rose white 5021

Blush 5044

Henna 5045

Mauve 5252

Creeksand 2150

Crimson 2310

Praline 2499



Walnut 2497



Café latte 2962



Loam 2216



Artichoke 7980



Oak 3650



Sandstone 2012



Spelt 2160



Green olive 7560



Flax 2971



Gobi 2987



Cactus 2975



Creeksand 2150




Plaster 2122



Linen 290



Moor 2490




Arabic 2972



Dark brown 2495



Pacific 5984



Midnight blue 5901




Black 0500



Sapphire 5830




Royal navy 5295




Red brick 4977




Red pepper 4268



Diamond red 4985



Bardolino 4650



Lilac 5252



Basalt 1060



Quartz 2123



Khaki 8975



Lemon 7520



**Milk Chocolate
2986**




Yellow ochre 8720



**Latte
macchiato 2230**



Avocado 7580



Zinfandel 4970

For Leather swatch, please contact JMT sales team.

GENERAL DETAILS

Category	Pigmented
Application	Furniture
Raw Material	European Hide
Country of Production	Italy
Average Hide Size sq ²	About 55
Average Thickness mm	0.9-1.0
Colour Checking	D65 Daylight
Appearance	Conform to the master

CHARACTERISTIC	TEST METHOD	M.U.	PERFORMANCE
Thickness	ISO2589	mm	0.9-1.0
Dry Rub Fastness	EN ISO 11640	Grey Scale	Dry 500 cycles > 4
Wet Rub Fastness	EN ISO 11640	Grey Scale	Wet 250 cycles > 3/4
Perspiration Rub Fastness	EN ISO 11640	Grey Scale	Perspiration 80 cycles > 3
Finishing Adhesion	EN ISO 11644	N/10 mm	>2
Flexing Endurance	EN ISO 5402	Visual	50,00 cycles (no cracks)
Colour Fastness to Light	EN ISO 105-B02	Blue Scale	>5
Tear Strength – Single edge	EN ISO 3377-1	N	>20
Tensile Strength	EN ISO 3376	N/mm ²	>10
Colour Fastness to Water Spotting	EN ISO 15700	Grey Scale	>3
pH and ΔpH	EN ISO 4045	Min 3,2 - ΔpH≤0.7 if pH<4	Pass
Burning Behaviour to cigarette and match flame	BS 5852:1979-BS EN 1021-1/ EN 1021-2		Pass
Chemical Characteristic	Article processed in conformity with Reach regulation		

LEATHER FEATURES AND CARE:

Characteristics not presented in this document are not applicable or not defined by producer. Additional requirements must be specified by the Customer before making the purchase order. Results of tested characteristics are an average of results found on standard productions. Eco and Environmental safety conformity to CE 1907/2006 REACH is assured until shipment. In case of further chemical treatments, it is the customer's responsibility to verify the chemical compatibility and that the chemicals used, do not impact on the conformity of the leather. JMT Leather will not respond legally in case of missed indications checking. Hides must be worked maintaining an internal humidity of the hide of 10-12% and using a process temperature not higher than 60°C/140°F to avoid any change of the hides mechanical properties and aspect. Do not put over weights on hides during stock, same goes for finished furniture. Stock hides and finished furniture in dry ambient with temperature 15/40°C - 59/104°F. Avoid using any solvent or lotion because they could weaken finishing adhesion. Heat guns shrink wrapping and any other source of heat must be avoided. Avoid using any wrapping/packing material that may react with the leather or finished furniture. Natural growth features, colour and structure differences (uneven appearance) are indications of genuineness (visible/clearly visible). Natural defects such as scars, growth marks and insect bites are normal hide characteristics and are not part of the leather production process. The initial leather smell is typical of the material. Colour and structure differences compared with the sample furniture and leather specimens are possible. To maintain the initial characteristics of goods produced with our articles, it is recommended to follow these instructions: keep them in dry ambient at room temperature. Keep leather away from sunlight and from any sources of heat to avoid colour change and darkening.

Use only recommended leather cleaner and protector products. Totally avoid multi-purpose cleaning products. Before using cleaning product, try it on a hidden surface. Clean stains as fast as possible; beverage stains could be removed dabbing with blotting paper without rubbing, then pass gently a white wet cloth on the stain, from external to internal side. After drying, polish it with a soft dry cloth. For domestic furniture, fully clean and re-protect your leather furniture at least every six months. For contract furniture, we recommend a regular cleaning and maintenance program as often as necessary.

We recommend leather maintenance products by LCK International in Germany.