



Technical Specification Sheet

TAPAS

WWW.JMTLEATHER.COM.CN

WWW.JMTLEATHER.COM

TAPAS COLLECTION:



A drum dyed, vacuum dried, full grain aniline leather with a light finish to give an even appearance. With a protective seal coat. Suitable for contract and domestic applications. Substance 1.0/1.1mm. Average size about 52/54 sqft. Made on UK Ox.

100% MADE IN ITALY.

COLOUR SELECTION:

						
PORCELAIN TP8025	BUFF TP8028	LINEN TP8024	STONE TP8027	DYR LEAF TP8052	PEBBLE TP8026	REED TP8051
						
BISCUIT TP8029	SAFFRON TP8045	AUTUMN TP8044	TOBACCO TP8043	OCHRE TP8042	CINNAMON TP8041	HEART BREAK TP8039
						
TABASCO TP8040	VINO TP8038	MELON TP8037	AUBERGINE TP8036	BAMBOO TP8023	HEMP TP8047	OLIVE TP8049



For Leather swatch, please contact JMT sales team.

GENERAL DETAILS

Category	Aniline
Application	Furniture
Raw Material	Top quality UK OX hides
Country of production	Italy
Average Hide Size sq ²	About 52/54
Average Thickness mm	1.0/1.1
Colour Checking	D65 Daylight
Appearance	Conform to the master

CHARACTERISTIC	TEST METHOD	M.U.	PERFORMANCE
Thickness	ISO2589	mm	1.0/1.1
Dry Rub Fastness	EN ISO 11640	Grey Scale	Dry 200 cycles > 4
Wet Rub Fastness	EN ISO 11640	Grey Scale	Wet 80 cycles > 3/4
Perspiration Rub Fastness	EN ISO 11640	Grey Scale	Perspiration 20 cycles > 3
Finishing Adhesion	EN ISO 11644	N/10 mm	>2
Flexing Endurance	EN ISO 5402	Visual	Dry 20,00 cycles (no cracks)
Colour Fastness to Light	EN ISO 105-B02	Blue Scale	>4
Tear Strength – Single edge	EN ISO 3377-2	N	>20
Tensile Strength	EN ISO 3376	N/mm ²	>10
Colour Fastness to Water Spotting	EN ISO 15700	Grey Scale	>3
pH and ΔpH	EN ISO 4045	Min 3,2 - ΔpH≤0.7 if pH<4	Pass
Burning Behaviour to cigarette and match flame	BS 5852:1979-BS EN 1021-1/ EN 1021-2		Pass
Chemical Characteristic	Article processed in conformity with Reach regulation		

LEATHER FEATURES AND CARE:

Characteristics not presented in this document are not applicable or not defined by producer. Additional requirements must be specified by the Customer before making the purchase order. Results of tested characteristics are an average of results found on standard productions. Eco and Environmental safety conformity to CE 1907/2006 REACH is assured until shipment. In case of further chemical treatments, it is the customer's responsibility to verify the chemical compatibility and that the chemicals used, do not impact on the conformity of the leather. JMT Leather will not respond legally in case of missed indications checking. Hides must be worked maintaining an internal humidity of the hide of 10-12% and using a process temperature not higher than 60°C/140°F to avoid any change of the hides mechanical properties and aspect. Do not put over weights on hides during stock, same goes for finished furniture. Stock hides and finished furniture in dry ambient with temperature 15/40°C - 59/104°F. Avoid using any solvent or lotion because they could weaken finishing adhesion. Heat guns shrink wrapping and any other source of heat must be avoided. Avoid using any wrapping/packing material that may react with the leather or finished furniture. Natural growth features, colour and structure differences (uneven appearance) are indications of genuineness (visible/clearly visible). Natural defects such as scars, growth marks and insect bites are normal hide characteristics and are not part of the leather production process. The initial leather smell is typical of the material. Colour and structure differences compared with the sample furniture and leather specimens are possible. To maintain the initial characteristics of goods produced with our articles, it is recommended to follow these instructions: keep them in dry ambient at room temperature. Keep leather away from sunlight and from any sources of heat to avoid colour change and darkening.

Use only recommended leather cleaner and protector products. Totally avoid multi-purpose cleaning products. Before using cleaning product, try it on a hidden surface. Clean stains as fast as possible; beverage stains could be removed dabbing with blotting paper without rubbing, then pass gently a white wet cloth on the stain, from external to internal side. After drying, polish it with a soft dry cloth. For domestic furniture, fully clean and re-protect your leather furniture at least every six months. For contract furniture, we recommend a regular cleaning and maintenance program as often as necessary.

We recommend leather maintenance products by LCK International in Germany.